Product Specification: Wallan Concrete Pre-Mixed Concrete – 25 MPa, 14mm Maximum Agg. Size

PRODUCT CODE: 120-N2514 NOMINAL STRENGTH: 25 MPa GRADE DESIGNATION: N25 CUSTOMER: Standard Product Standard Product N25

REFERENCE: AS1379 – Specification and Supply of Concrete

Compliance Requirements for Product Constituents

compliance requirements for Froduct constituents							
Constituent	Compliant With	Constituent	Compliant With				
20mm SS Agg	AS 2758.1	Mixing Water	AS 1379.2.4				
14/10 Class GP Agg	AS 2758.1	Chemical Admixtures	AS 1487				
Coarse Sand	AS 2758.1	Fly Ash	AS 3582.1				
Fine Sand	AS 2758.1	Slag	AS 3582.2				
GP Cement	AS 3972	Batch Ingredients Tolerances	AS 1379.4.2				

Tests Carried Out For Production Control (Control Grade)							
Test	Sample Method	Test Method	Frequency	Requirements	Reference		
Slump	AS1012.1	AS1012.3.1	1 per Strength Sample 1 per 100m ³	As per AS1379: Table 5.1	AS1379.5.2		
28-day Strength	AS1012.1	AS1012.9	1 per 100m ³ (2 cylinders)	$Mean (f_{cm}) \ge f'_{c} + k_{c}s$	AS1379.6.3		
7-day Strength	AS1012.1	AS1012.9	1 per 100m ³ (1 Cylinder)	Mean for Production Interval ≥ 12MPa	AS1379.5.7		
Air Content	AS1012.1	AS1012.4.2	1 per 6 months	±1.5% of Mix Design Air Content	AS1379.5.4		
Chloride and Sulfate Content	AS1012.1	AS1012.20	1 per 6 months	Chloride-ion ≤ 0.8 kg/m3 Sulfate-ion ≤ 50 g/kg	AS1379.5.5		
Drying Shrinkage	AS1012.1 or AS1012.2	AS1012.13	1 per 6 months	≤ 1000 µS	AS1379.5.6		
Mass Per Unit Volume	AS 1012.1	AS1012.5	1 per 6 months	≥ 98% Specified Volume	AS1379.1.7.2		

Tests Carried Out on Water							
Test	Sample Method	Test Method	Frequency	Requirements	Reference		
Sugar	AS/NZS 5667.10	AS1141.35	1 per 6 months	≤100mg/L	AS1379.2.4		
Oil and Grease	AS/NZS 5667.10	APHA 5520	1 per 6 months	≤50mg/L	AS1379.2.4		
рН	AS/NZS 5667.10	AS/NZS 1580.505.1	1 per 6 months	>5.0	AS1379.2.4		
Total Dissolved Solids	AS/NZS 5667.10	AS3550.4	1 per 6 months	≤2000mg/L	AS1379.2.4		